



all solutions in one partner®

## SCHEDA TECNICA - CODICE NAF07001-05



### NASTRO BIADESIVO CON PELLICOLA SINGOLA SUPERPROFESSIONALE

Nella posa in opera di pareti divisorie, per fissaggio delle guide alla pavimentazione (ove necessita non forare). Per un'azione combinata di rapido fissaggio e abbattimento acustico, in resina di polietilene impermeabile e imputrescibile, non tossico.



CODICE	LUNGHEZZA [m]	LARGHEZZA [mm]	SPESSORE [mm]	PZ/ CONFEZIONE	BANCALI/ ROTOLI
NAF07001	20	30	3	380	9120
NAF07002	20	40	3	280	6720
NAF07003	20	50	3	240	5760
NAF07004	20	70	3	180	4320
NAF07005	20	95	3	120	2880

### CARATTERISTICHE MATERIALE

PROPRIETÀ	VALORE	U.d.M.	METODO
MATERIALE	Polietilene espanso reticolato a celle chiuse	/	/
DENSITÀ	29	Kg/m <sup>3</sup>	ISO-485
COLLA	Gomma termoplastica	/	/
SPESSORE	3	mm	/
TEMPERATURA DI UTILIZZO	-5/80	°C	/
RESISTENZA ALLA TENSIONE (rif. Lunghezza)	380	kPa	ISO-1926
RESISTENZA ALLA TENSIONE (rif. Larghezza)	230	kPa	ISO-1926
ALLUNGAMENTO (rif. Lunghezza)	120	%	ISO-1926
ALLUNGAMENTO (rif. Larghezza)	110	%	ISO-1926
COMPRESSIONE (dopo 24h)	11.8	%	ISO-1856-C
ASSORBIMENTO DELL'ACQUA	1	%	ISO-2896
CONSERVABILITÀ (temperatura ambiente)	1	anno	/



all solutions in one partner®

# DATA SHEET - CODE NAF07001-05



## DOUBLE-SIDED TAPE WITH SINGLE SUPER-PROFESSIONAL FILM

In the installation of partition walls, for fixing rails to the floor (where it is necessary not to drill holes). For a combined fastening and soundproofing action, in waterproof and rot-proof, non-toxic polyethylene resin.



CODE	LENGTH [m]	WIDTH [mm]	THICKNESS [mm]	PCS PER BOX	PALLET/ PCS
NAF07001	20	30	3	380	9120
NAF07002	20	40	3	280	6720
NAF07003	20	50	3	240	5760
NAF07004	20	70	3	180	4320
NAF07005	20	95	3	120	2880

## MATERIAL FEATURES

FEATURE	VALUE	U.o.M.	METHOD
MATERIAL	Polyethylene foam, physically crosslinked	/	/
DENSITY	29	Kg/m3	ISO-485
GLUE	Thermoplastic rubber	/	/
THICKNESS	3	mm	/
OPERATING TEMPERATURE	-5/80	°C	/
STRESS STRENGTH (ref. Length)	380	kPa	ISO-1926
STRESS STRENGTH (ref. Width)	230	kPa	ISO-1926
ELONGATION (ref. Length)	120	%	ISO-1926
ELONGATION (ref. Width)	110	%	ISO-1926
COMPRESSION (after 24h)	11,8	%	ISO-1856-C
WATER ABSORPTION	1	%	ISO-2896
PRESERVABILITY (dry at room temperature)	1	year	/